

## PELLET SPECIFICATION

The specification of AGI pellets will be driven by customer requirements, but will be in line with EN Plus and DIN Plus standards.

	<b>ENplus</b>	<b>DINplus</b>
Diameter (mm)	6 ± 1,0 to 8 ± 1,0	6 ± 1,0 to 8 ± 1,0
Length (mm)	3,15 ≤ L ≤ 40	3,15 ≤ L ≤ 40
Calorific value (MJ/kg)	16,5 ≤ Q ≤ 19,0	16,5 ≤ Q ≤ 19,0
Water content (%)	≤ 10,0	≤ 10,0
Fines (%)	≤ 1,0	≤ 1,0
Abrasion (%)	≤ 2,5	≤ 2,3
Ash content (%)	≤ 0,7	≤ 0,7
Ash softening temperature (C)	≥ 1200	not specified
Pressing aid (%)	≤ 2,0	≤ 2,0
Flow density (kg/m <sup>3</sup> )	≥ 600	≥ 600
Sulfur content (%)	≤ 0,03	≤ 0,03
Nitrogen content (%)	≤ 0,3	≤ 0,3
Chlorine content (%)	≤ 0,02	≤ 0,02